




Area of use*



Technical features

Protective gloves.

Liner: high density polyethylene and glass fibers, seamless knitted.

Gauge: 13.

Wrist: elastic knit with piping.

Lining: acrylic terry.

Double coating.

First layer: smooth nitrile, coated on palm.

Second layer: sandy nitrile foam, coated on palm.

Colour: white, black and grey.


Sizes: 8 to 11.

Packaging: carton of 50 pairs.

Subpackaging: bag of 5 pairs.

Advantages

- Excellent cut resistance** with the technical fibers of the liner.
- Insulation and comfort** with the lining.
- Oil resistance** with the nitrile coating.
- Excellent sealing** with the double coating.
- Quality and reliability** of ISO 9001 / ISO 14001 certified production.
- Screentouch gloves.**




Certification

This product complies with **European Regulation (EU) 2016/425** on Personal Protective Equipment (PPE). **Category II.**

Issued by **MIRTA-KONTROL d.o.o.**, notified body n°2474.

EN 388 : 2016 + A1 : 2018



EN ISO 21420 : 2020


4X43D

EN 407 : 2020



X2XXXX

EN 511 : 2006



X2X



Download the EU declaration of conformity on <http://docs.singer.fr>

EN ISO 21420 - PROTECTIVE GLOVES

General requirements and test methods. This standard specifies the essential requirements for ergonomics, safety, marking, information and instructions for use.

EN 388 - AGAINST MECHANICAL RISKS



1.2.3.4.F.P

1	Abrasion resistance. Level 1 to 4 (4 being the best).
2	Blade cut resistance. Level 1 to 5 (5 being the best).
3	Tear resistance. Level 1 to 4 (4 being the best).
4	Puncture resistance. Level 1 to 4 (4 being the best).
F	Cut resistance (ISO13997). Level A to F (F being the best).
P	Resistance against impact (according to EN 13594). Marking P (optional test).

For gloves that contain materials which can get dulls to the blade, and additional compulsory test must be performed according to EN ISO 13997 test method (TDM 100 tester).
This test may also be optional for gloves that do not dull the blade.

EN 374 - AGAINST CHEMICALS



Type X
X.X.X

A	Type A	Breakthrough time \geq 30 min for at least 6 chemicals of the list (see below)	
	Type B	Breakthrough time \geq 30 min for at least 3 chemicals of the list (see below)	
	Type C	Breakthrough time \geq 10 min for at least 1 chemical of the list (see below)	
A	Methanol	67-56-1	Primary alcohol
B	Acetone	67-64-1	Ketone
C	Acetonitrile	75-05-8	Nitrile composite
D	Dichloromethane	75-09-2	Chlorinated hydrocarbon
E	Carbone Disulphide	75-15-0	Organic compound containing Sulphur
F	Toluene	108-88-3	Aromatic hydrocarbon
G	Diethylamine	109-89-7	Amine
H	Tetrahydrofurane	109-99-9	Heterocyclic Ether
I	Ethyl acetate	141-78-6	Ester
J	n-Heptane	142-82-5	Saturated Hydrocarbon
K	Sodium hydroxide 40%	1310-73-2	Inorganic base
L	Sulphuric acid 96%	7664-93-9	Inorganic mineral acid, oxidising
M	Nitric acid (65±3) %	7697-37-2	Inorganic mineral acid
N	Acetic acid (99±1) %	64-19-7	Organic acid
O	Ammonia 25%	1336-21-6	Organic base
P	Hydrogen peroxid 30%	7722-84-1	Peroxide
S	Hydrofluoric acid 40%	7664-39-3	Inorganic mineral acid
T	Formaldehyde 37%	50-00-0	Aldehyde
	Classe 1	Breakthrough time: > 10 minutes	
	Classe 2	Breakthrough time: > 30 minutes	
	Classe 3	Breakthrough time: > 60 minutes	
	Classe 4	Breakthrough time: > 120 minutes	
	Classe 5	Breakthrough time: > 240 minutes	
	Classe 6	Breakthrough time: > 480 minutes	

ASTM F2878 - PUNCTURE RESISTANCE TO AN HYPODERMIC NEEDLE



Level 1	Puncture resistance with a less or an equal force to 2 N.
Level 2	Puncture resistance with a less or an equal force to 4 N.
Level 3	Puncture resistance with a less or an equal force to 6 N.
Level 4	Puncture resistance with a less or an equal force to 8 N.
Level 5	Puncture resistance with a less or an equal force to 10 N.

EN 374-5 - AGAINST MICRO-ORGANISMS



VIRUS

Protection against bacteria and fungi

VIRUS = with additional permeation test to virus (ISO16604)

EN 511 - AGAINST THE COLD



A.B.C

A	Convective cold. Level 0 to 4 (4 being the best).
B	Contact cold. Level 0 to 4 (4 being the best).
C	Waterproofness. Level 0 (No) or 1 (Yes).

EN 407 - AGAINST THERMAL RISKS (HEAT AND/OR FIRE)



A.B.C.D.E.F



X.B.C.D.E.F
(*) Max Level 2

A	Burning behaviour. Level 1 to 4 (4 being the best).
B	Contact heat (threshold time \geq 15 s). Level 1 to 4 (4 being the best). 1= 100°C / 2= 250°C / 3= 350°C / 4= 500°C
C	Convective heat. Level 1 to 4 (4 being the best).
D	Radiant heat. Level 1 to 4 (4 being the best).
E	Small splashes of molten metal. Level 1 to 4 (4 being the best).
F	Large splashes of molten metal. Level 1 to 4 (4 being the best).

EN 12477 + A1 - FOR WELDERS

Type A

More general welding and cutting operations

Type B

Higher dexterity for TIG welding

ISO 18889 - PESTICIDE HANDLING



X

G1
Low potential risk. Diluted pesticides.
Without mechanical resistance.

G2
Medium potential risk. Diluted or concentrated pesticides.
Minimum mechanical resistance.

GR
Palm protection only.
Dry residues of pesticides.

EN ISO 10819 - VIBRATION AND MECHANICAL SHOCKS

Hand-arm vibration. Measurement and evaluation
of the vibration transmissibility from gloves to the palm of the hand.

EN 16350 - ELECTROSTATIC PROPERTIES



Each individual measurement shall satisfy:
the vertical resistance requirement: $R_v < 1,0 \times 10^8 \Omega$.
Test method according to EN 1149-2: 1997.



EN 60903 - MAXIMAL TENSION OF USE

	AC	DC	Class
750 V	500 V	00	
1 500 V	1 000 V	0	
11 250 V	7 500 V	1	
25 500 V	17 000 V	2	
39 750 V	26 500 V	3	
54 000 V	36 000 V	4	

"X" means that the glove has not been submitted to the test.